

GX-2005

UHS finish

FEATURES

- UHS finish
- Reduces labor costs
- Burnishes to a rich deep gloss

BENEFITS

- Excellent gloss and durability
- Extends recoat and strip-out cycles
- Maintains clarity and color

RECOMMENDED USES

For use on all resilient floors.

SPECIFICATIONS

Color : White
Scent/Odor : Solvent
Character : Opaque, non-viscous liquid
Foam : Non-foamer

pH use dilution : 8.0 - 9.0
Phosphorus content : 0.19%
Approvals : None



IMPORTANT

Read and understand the label and Safety Data Sheet (SDS). These provide a description of hazards, precautions, personal protective equipment, first aid, 24 Hour Emergency lines, storage data and other safe handling information. The SDS is available on our website at www.uschemical.com and is also available by scanning the QR code on the label.

PRODUCT DIRECTIONS

EQUIPMENT TO USE

Appropriate stripping chemicals and equipment, dust mop, clean mop, mop bucket, automatic scrubber and wet floor signs.

DIRECTIONS TO USE

1. Blockade area to be stripped or finished. Floors will be very slippery until dry.
2. Strip floor using Misco Genesis Ice-Strip or another appropriate Misco Genesis product per the instructions on the label.

INITIAL COATING:

1. Apply 3 or more coats of GX-2005 with a clean finish mop. Apply additional coats until desired gloss is obtained. On porous resilient or stone floors seal with 2 coats of recommended sealer.
2. Allow approximately 30-45 minutes of drying time between coats. Temperature, humidity and ventilation may affect drying time. Allow finish to cure for 24 hours before burnishing.

FLOOR MAINTENANCE:

1. Dust mop or sweep daily with microfiber dust mop.
2. Clean the floor daily with a mop or automatic scrubber using a recommended neutral cleaner according to the label directions.
3. To enhance appearance burnish with appropriate pads.

SCRUB & RECOAT:

1. Prior to recoating, dust mop area with preferred microfiber dust mop or sweep.
2. Clean the floor with an automatic scrubber or low speed machine with a blue or green cleaning pad. Use a recommended neutral cleaner or all purpose cleaner according to the label directions.
3. Blockade area and apply 1 - 2 uniform coats of GX-2005 using a finish mop.
4. Allow finish to cure for 24 hours before burnishing.

PACKAGING

This product is available in a 5 gallon BIB (100938696).